

UNIROLL PLUS GLASS WOOL ROLLS ISOVER



BENEFITS

- very good thermal insulation performance (low thermal conductivity)
- fire safety - non-combustible material
- excellent acoustic properties (high absorption coefficient)
- easy to handle, non-toxic
- easy installation in roof and wooden structures—the product is elastic and compressible
- easy installation in roof and wooden structures— a piece of product that is 2 cm wider than the distance between rafters stays without any support between them
- at installation can be pierced by the hangers of the dry lining system - this eliminates the spaces without insulation material around them, which represents thermal bridges
- low vapour flow resistance
- unlimited resistance in vertical position
- environment friendly and hygienic
- completely hydrophobic - is made water repellent
- long life span and time-stable properties
- resistant to mould, mildew, rodents and insects
- chemically neutral, non-corrosive
- easy workability - can be cut, drilled etc

TECHNICAL SPECIFICATION

Compressed rolls made of Isover glass wool. The mats are manufactured by melting the mineral raw materials in a furnace, fiberizing the melt through TEL process, spraying a binder and adding mineral oils for protection against dust and water repellence. The mineral fibres mat is compressed and packaged in rolls on the production line.

APPLICATION

Isover UNIROLL PLUS mats can be used for thermal and sound insulation of residential buildings where insulation is not subject to mechanical loads:

- pitched roofs and attics
- walls of wooden houses
- the inner surface of vertical walls
- attic floors.



RELATED DOCUMENTS

EC compliance certificate:
CE 1840 -CPR- 99/91/EC/0677-18
ISO 9001
ISO 14001
ISO 45001
Certificat EUCB
Environmental Product Declaration (EPD®)

UNIROLL PLUS

GLASS WOOL ROLLS ISOVER



TECHNICAL PARAMETERS

PARAMETER	U.M.	VALUE
THERMAL INSULATION PROPERTIES		
Declared thermal conductivity - λ_D	W/(m*K)	0.036
FIRE SAFETY PROPERTIES		
Reaction to fire	-	A1
OTHER PROPERTIES		
Air flow resistivity AFr	kPa * s/m2	>9
Water vapour diffusion resistance factor, μ	-	1
Maximum temperature for use	°C	200

SIZE AND PACKAGING

Product	Thickness (mm)	Length x width (mm)	Area (m ² /roll)	Declared thermal resistance R_D (m ² ·K/W)
UNIROLL PLUS	2 x 50	5000 x 1200*	12	1.35
UNIROLL PLUS	100	5000 x 1200	6	2.75
UNIROLL PLUS	120	4500 x 1200	5.4	3.30
UNIROLL PLUS	150	4500 x 1200	5.4	4.15
UNIROLL PLUS	180	4500 x 1200	5.4	5.00
UNIROLL PLUS	200	4000 x 1200	4.8	5.55

* rols with 2 mats

ISOVER is a registered trademark of Saint-Gobain. The information contained herein reflects the latest data based on our current knowledge and experience and are subject to change without prior notice as a result of technical or production changes. Please ensure you always have the latest version of this document by accessing our site at the following address: www.isover.ro.
This document contains only general recommendations and does not address special circumstances.

Prior to installation, please ensure that you have thoroughly read and understood the specifications of your project, that you have tested the product for your specific purpose, and that the selected product will enable the required outcome.
The information presented in this document does not constitute a guarantee as to certain properties of the product or compatibility for a specific use, hence Saint-Gobain Group cannot be held responsible for the quality of the installation works.

SAINT-GOBAIN ROMANIA • ISOVER
Șos. Pipera nr. 43
Clădirea Floreasca Park • Corp A • etaj 3
Sector 2 • București • România
Tel: +40 (21) 207 57 50/51
www.isover.ro

